



BSI Standards Publication

<http://www.china-gauges.com/>

Bituminous mixtures — Test methods

Part 7: Determination of the bulk density of bituminous specimens by gamma rays

National foreword

This British Standard is the UK implementation of EN 12697-7:2022 and supersedes BS EN 12697-7:2014, which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/510/1, Asphalt products.

A list of organizations represented on this committee can be obtained on request to its committee manager.

Contractual and legal considerations

This publication has been prepared in good faith, however no representation, warranty, assurance or undertaking (express or implied) is or will be made, and no responsibility or liability is or will be accepted by BSI in relation to the adequacy, accuracy, completeness or reasonableness of this publication. All and any such responsibility and liability is expressly disclaimed to the full extent permitted by the law.

This publication is provided as is, and is to be used at the recipient's own risk.

The recipient is advised to consider seeking professional guidance with respect to its use of this publication.

This publication is not intended to constitute a contract. Users are responsible for its correct application.

© The British Standards Institution 2022
Published by BSI Standards Limited 2022

ISBN 978 0 539 15309 5

ICS 93.080.20

Compliance with a British Standard cannot confer immunity from legal obligations.

This British Standard was published under the authority of the Standards Policy and Strategy Committee on 31 March 2022.

Amendments/corrigenda issued since publication

Date	Text affected
------	---------------

EUROPEAN STANDARD

EN 12697-7

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2022

ICS 93.080.20

Supersedes EN 12697-7:2014

English Version

Bituminous mixtures - Test methods - Part 7:
Determination of the bulk density of bituminous
specimens by gamma rays

Mélanges bitumineux - Méthodes d'essai - Partie 7 :
Détermination de la masse volumique apparente des
éprouvettes bitumineuses par les rayons gamma

Asphalt - Prüfverfahren - Teil 7:
Bestimmung der Raumdichte von Asphalt-
Probekörpern mit Gamma-Strahlen

This European Standard was approved by CEN on 26 December 2021.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword	iii
Introduction	iv
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle	5
5 Apparatus	5
6 Preparation of specimens	6
7 Procedure	6
7.1 Prior adjustments	6
7.2 Choice of beam diameter	6
7.3 Measurement procedure	7
7.3.1 Measurement mode	7
7.3.2 Continuous measurements	7
7.3.3 Localized or point measurements	8
8 Expression of results	8
9 Test report	9
10 Precision	9
Bibliography	10

European foreword

This document (EN 12697-7:2022) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2022, and conflicting national standards shall be withdrawn at the latest by August 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12697-7:2014.

The main changes compared to the previous edition are listed below:

- the title no longer refers to hot mix asphalt;
- [ge] editorial update according to current standard template;
- [Clause 1](#), scope clarified according the CEN/CENELEC Internal Regulations Part 3:2019, 14.5;
- [Clause 4](#), deletion of the exponential law including equation. Added reference to [Clause 8](#);
- [\(5.1\)](#), footnote 1) amended to NOTE. Existing NOTE amended to normal text;
- [Clause 6](#), NOTE 1: The period for when specimens are considered to be dry amended to 4 h in line with other parts;
- [Clause 6](#), Footnote 2) amended to NOTE 2. Existing NOTE amended to NOTE 1;
- [Clause 6](#), measurement of the thickness of specimen replaced by "shall be known";
- [\(7.3.3\)](#), formula for consistency test deleted and replaced with reference to [Formula \(1\)](#);
- [Clause 8](#), editorial adjustments, renumbered formulas and addition of references to formulas;
- [Clause 9](#), revision of data to be reported;
- [Clause 10](#), completion of standard edition to read ISO 5725-2;
- [ge] bibliography added.

A list of all parts in the EN 12697 series can be found on the CEN website.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Bulk density measurement in the laboratory using gamma rays is a method which does not affect the properties of the material. It can be included in a series of tests carried out on a given sample. It allows the plotting of a density chart or gradient.

<http://www.china-gauges.com/>

1 Scope

This document specifies a method for measuring the bulk density of pavement mixtures using a transmission-type gamma radiation test bench.

This method applies to cylindrical specimens or parallelepipedal blocks, prepared in a laboratory or cut from a pavement. The thickness and the mass absorption coefficient, which is a function of the chemical composition, are known. The thickness of the specimen body traversed by the radiation is between 30 mm and 300 mm.

The method cannot be applied to materials containing slags, with variable metal content or chemical composition.

NOTE Material containing metal or chemical compositions can affect the absorption of gamma rays.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12697-6, *Bituminous mixtures - Test methods - Part 6: Determination of bulk density of bituminous specimens*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Principle

The method is based upon the absorption of gamma radiation by the material under the conditions of the test described in this document and for materials such as bituminous mixtures. The method follows an exponential law according to [Clause 8, Formulae \(2\) and \(3\)](#).

The specimen is placed in the path of a gamma ray beam coming from an emitting unit containing a radioactive source and having a collimation corridor. A photomultiplier in the receiving unit transforms the incident photons into pulses with amplitudes proportional to their energy. An electronic system performs the functions allowing the different applications.

5 Apparatus

The safety regulations applicable to the use of gamma rays apply.

5.1 Emitter-source unit and receiving unit, at a fixed distance in relation to each other during the measurement. The axis of the gamma radiation beam and that of the receiver shall coincide.

NOTE A radioactive source of Cs 137 with an energy level of 0,662 MeV is suitable for this purpose.

Two cases are possible:

- the emitter and receiver are fixed and the specimens move between them;

— the specimens are fixed and the emitter-receiver assembly moves in relation to them.

In both cases, during the measurement the apparatus allows the rotation of cylindrical specimens about themselves or the relative translation of the specimens having at least one flat side.

5.2 Several lead collimators, whose diameter is known to within 1 %.

5.3 Measurement chain including a count unit and a processing chain, the count unit and the processing chain shall be stabilized electronically against the effect of temperature variations.

5.4 Technical note, with nomograms allowing the determination of the measurement time yielding the requested precision.

The calibration coefficient (k) of the apparatus shall be checked periodically using a specimen with a known density according to the instructions given in the equipment user's manual: it shall be between 0,990 and 1,010 and shall remain constant to within 0,005, for a given diameter of the gamma radiation beam.

6 Preparation of specimens

Specimens shall have a known water content or be dry. If necessary, dry them at ambient temperature.

NOTE 1 Specimens are considered to be dry when the relative mass variation is less than 0,1 % per period of 4 h.

Specimens with one or more bituminous mix layers shall be placed on a flat and horizontal surface to avoid any deformation. The height of the part of each specimen on which density can be measured shall be noted on the test sheet.

In the case of specimens made in the laboratory, the top of the specimens shall be marked.

The surfaces analysed shall be rid of any foreign matter that may be clinging to them.

The thickness of material penetrated by the radiation shall be known to the nearest 0,1 mm.

NOTE 2 The uncertainty on the measurement of density is larger than the uncertainty on the measurement of the thickness of the material.

7 Procedure

7.1 Prior adjustments

Before performing a bulk density measurement or a series of measurements on a specimen, the following adjustments shall be carried out in accordance with instructions given by the manufacturer and in particular:

- alignment of different elements (if required);
- adjustment of the measurement chain.

7.2 Choice of beam diameter

At the outlet of the source support, place, as required, a collimator with a diameter equal or slightly smaller than that of the source.

In front of the detection unit place a 10 mm collimator, or, if the apparatus is such that the collimator can be changed, place:

- a 5 mm collimator to measure the density of layers for thickness less than or equal to 40 mm in the direction perpendicular to the beam;
- a 10 mm collimator to measure the density of layers for thicknesses greater than 40 mm in the direction perpendicular to the beam with materials whose maximum size is less than or equal to 14 mm;
- a 20 mm collimator to measure the density of layers for thicknesses greater than 40 mm in the direction perpendicular to the beam, with material whose maximum size is greater than 14 mm.

7.3 Measurement procedure

7.3.1 Measurement mode

Either of the following methods shall be used:

- a) continuous measurements: During the measurement, the specimen to be analysed is moved along a direction perpendicular to the radiation;
- b) localized or point measurements: There is no movement of the material during the measurement except for the axial rotation of cylindrical specimens explored radially.

7.3.2 Continuous measurements

- Measure the count rate in the absence of the material to be tested C_{01} .
- Calculate the integration time constant and the speed of the specimen in relation to the beam that yields the required accuracy, using the nomograms furnished in the test bench instructions.
- Set the sample on the specimen passer.
- Record the count rate (C) through the material during the movement of the specimen.
- Measure the count rate in the absence of the material to be tested C_{02} under the same conditions as the determination of C_{01} .
- The counts in the absence of the material to be tested shall be determined immediately before (C_{01}) and immediately after (C_{02}) passing the specimen.
- The count consistency test is given by [Formula \(1\)](#):

$$\frac{|C_{01} - C_{02}|}{\sqrt{\frac{C_{01} + C_{02}}{t}}} \leq 1,96 \quad (1)$$

where

C_{01}, C_{02} is the count rate (ratio of N_{01} or N_{02} to count time) in the absence of the material to be tested (in the air or in a reference specimen body, e.g. aluminium) before penetration into the material in counts per second, during the measurement number 1 or 2;

N_{01}, N_{02} is the number of gamma photons of the incident radiation measured in the absence of the material to be tested (in the air or in a reference specimen body, e.g. aluminium) before penetration into the material in counts per second, during the measurement number 1 or 2;

t is the measurement time, in seconds (s).

shall be verified.

7.3.3 Localized or point measurements

- Measure the count rate in the absence of the material to be tested C_{01} . Using the nomograms of the test bench instructions, in which the parameters are the count rate in the absence of material to be tested, the estimated density and the thickness of the specimen, determine the count time in absence of the material and through the material compatible with the required accuracy.
- In the case of a cylindrical specimen, ensure that the measurement is carried out during the rotation of the specimen. The specimen shall make at least one revolution, at constant speed, during the measurement.
- Carry out the measurement of C_{01} on the specimen making sure the edge of the gamma ray beam is at a distance of more than 3 mm from the sides of the specimen.
- Measure (C_{02}) in the absence of the material to be tested to check for drift.
- The count consistency test according to [Formula \(1\)](#) shall be verified.

8 Expression of results

Calculate the overall mass absorption coefficient (μ') by determining the weighted average of the coefficients as a function of the mass proportion of each element in the material including water. If the water content of the material is less than 4 %, the mass of water for the calculation of μ' may be ignored. The factor k can also be determined by back calibration; for this purpose, the density of a sample of material of the same chemical composition shall be measured in accordance with EN 12697-6.

The bulk density of the material, including water if the specimen is not dry, shall be given by the [Formula \(2\)](#) if C_{01} and C_{02} are count rates in the air:

$$\rho_{b\gamma} = \frac{10}{k\mu'd} \times \ln \left(\frac{C_{01} + C_{02}}{2C} \right) \quad (2)$$

where

- $\rho_{b\gamma}$ is the bulk density, in megagrams per cubic metre (Mg/m³);
- k is the calibration coefficient;
- μ' is the mass absorption coefficient (depending on composition of the mixture);
- d is the thickness of the mixture traversed by the radiation, in millimetres (mm);
- C_{01}, C_{02} is the count rate (ratio of N_{01} or N_{02} to count time) in the absence of the material to be tested (in the air or in a reference specimen body, e.g. aluminium) before penetration into the material in counts per second, during the measurement number 1 or 2;
- N_{01}, N_{02} is the number of gamma photons of the incident radiation measured in the absence of the material to be tested (in the air or in a reference specimen body, e.g. aluminium) before penetration into the material in counts per second, during the measurement number 1 or 2;
- C is the count rate after going through the mixture (ratio of N to count time), in counts per second.

If C_{01} and C_{02} are count rates in a reference body of thickness d_{ref} , absorption coefficient μ_{ref} and density ρ_{ref} , the bulk density shall be given by [Formula \(3\)](#).

$$\rho_{b\gamma} = \rho_{ref} \frac{\mu_{ref} d_{ref}}{\mu' d} + \frac{10}{k\mu'd} \times \ln \left(\frac{C_{01} + C_{02}}{2C} \right) \quad (3)$$

where

ρ_{by}	is the bulk density, in megagrams per cubic metre (Mg/m ³);
ρ_{ref}	is the density of the reference body, in megagrams per cubic metre (Mg/m ³);
μ'_{ref}	is the mass absorption coefficient of the reference body;
d_{ref}	is the thickness of the reference body, in millimetres (mm);
d	is the thickness of material traversed by the radiation, in millimetres (mm);
k	is the calibration coefficient;
μ'	is the mass absorption coefficient (depending on composition of the mixture);
C_{01}, C_{02}	is the count rate (ratio of N_{01} or N_{02} to count time) in the absence of the material to be tested (in the air or in a reference specimen body, e.g. aluminium) before penetration into the material in counts per second, during the measurement number 1 or 2;
C	is the count rate after going through the mixture (ratio of N to count time), in counts per second.

9 Test report

The test report shall include at least the following information:

- nature of the specimen and its identification;
- reference to this document;
- main parameters of the determination (beam diameter, type of apparatus and the measurement mode);
- appearance, any irregularities, the dimensions of the specimen and the dimensions of the measured zone;
- average bulk density, and if applicable, the density distribution chart;
- any deviations from the procedure;
- the date of the test.

10 Precision

The precision was determined according to ISO 5725-2 on a 10 mm asphalt concrete core having a bulk density of 2,294 Mg/m³ by 21 laboratories in France in March 2003 as being:

Repeatability: $r = 0,007 \text{ Mg/m}^3$

Reproducibility: $R = 0,02 \text{ Mg/m}^3$

Bibliography

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results - Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

<http://www.china-gauges.com/>

<http://www.china-gauges.com/>

British Standards Institution (BSI)

BSI is the national body responsible for preparing British Standards and other standards-related publications, information and services.

BSI is incorporated by Royal Charter. British Standards and other standardization products are published by BSI Standards Limited.

About us

We bring together business, industry, government, consumers, innovators and others to shape their combined experience and expertise into standards-based solutions.

The knowledge embodied in our standards has been carefully assembled in a dependable format and refined through our open consultation process. Organizations of all sizes and across all sectors choose standards to help them achieve their goals.

Information on standards

We can provide you with the knowledge that your organization needs to succeed. Find out more about British Standards by visiting our website at bsigroup.com/standards or contacting our Customer Services team or Knowledge Centre.

Buying standards

You can buy and download PDF versions of BSI publications, including British and adopted European and international standards, through our website at bsigroup.com/shop, where hard copies can also be purchased.

If you need international and foreign standards from other Standards Development Organizations, hard copies can be ordered from our Customer Services team.

Copyright in BSI publications

All the content in BSI publications, including British Standards, is the property of and copyrighted by BSI or some person or entity that owns copyright in the information used (such as the international standardization bodies) and has formally licensed such information to BSI for commercial publication and use.

Save for the provisions below, you may not transfer, share or disseminate any portion of the standard to any other person. You may not adapt, distribute, commercially exploit or publicly display the standard or any portion thereof in any manner whatsoever without BSI's prior written consent.

Storing and using standards

Standards purchased in soft copy format:

- A British Standard purchased in soft copy format is licensed to a sole named user for personal or internal company use only.
- The standard may be stored on more than one device provided that it is accessible by the sole named user only and that only one copy is accessed at any one time.
- A single paper copy may be printed for personal or internal company use only.

Standards purchased in hard copy format:

- A British Standard purchased in hard copy format is for personal or internal company use only.
- It may not be further reproduced – in any format – to create an additional copy. This includes scanning of the document.

If you need more than one copy of the document, or if you wish to share the document on an internal network, you can save money by choosing a subscription product (see 'Subscriptions').

Reproducing extracts

For permission to reproduce content from BSI publications contact the BSI Copyright and Licensing team.

Subscriptions

Our range of subscription services are designed to make using standards easier for you. For further information on our subscription products go to bsigroup.com/subscriptions.

With **British Standards Online (BSOL)** you'll have instant access to over 55,000 British and adopted European and international standards from your desktop. It's available 24/7 and is refreshed daily so you'll always be up to date.

You can keep in touch with standards developments and receive substantial discounts on the purchase price of standards, both in single copy and subscription format, by becoming a **BSI Subscribing Member**.

PLUS is an updating service exclusive to BSI Subscribing Members. You will automatically receive the latest hard copy of your standards when they're revised or replaced.

To find out more about becoming a BSI Subscribing Member and the benefits of membership, please visit bsigroup.com/shop.

With a **Multi-User Network Licence (MUNL)** you are able to host standards publications on your intranet. Licences can cover as few or as many users as you wish. With updates supplied as soon as they're available, you can be sure your documentation is current. For further information, email cservices@bsigroup.com.

Revisions

Our British Standards and other publications are updated by amendment or revision.

We continually improve the quality of our products and services to benefit your business. If you find an inaccuracy or ambiguity within a British Standard or other BSI publication please inform the Knowledge Centre.

Useful Contacts

Customer Services

Tel: +44 345 086 9001

Email: cservices@bsigroup.com

Subscriptions

Tel: +44 345 086 9001

Email: subscriptions@bsigroup.com

Knowledge Centre

Tel: +44 20 8996 7004

Email: knowledgecentre@bsigroup.com

Copyright & Licensing

Tel: +44 20 8996 7070

Email: copyright@bsigroup.com

BSI Group Headquarters

389 Chiswick High Road London W4 4AL UK